

Indicus Forto

DURABLE EXTERIOR EMULSION



Anti-aging paint that resists all forces of nature for a longer period.



Dura-colour technology

Innovative technology that enhances the performance of the paint by resisting all forces of nature.



Anti-stress

Optimized composition that resists against different stress factors, including chemicals such as efflorescence and alkali.



UV resistant

Gives good protection from UV degradation that makes the paint last longer.



Fresh & clean look

Perfect paint film and optimized surface that resists dirt and pollution settling on the walls.



Superior anti-algal

Designed for long-term protection against algae and fungi growth on walls.



8 years protection*

8 years performance warranty for film integrity, flaking and peeling.



INDICUS FORTO is a high-performance exterior emulsion formulated with innovative Dura-colour Technology. It resists all forces of nature to keep the look of the house fresh and clean for a longer period of time.

Technical Properties

Finish	Rich sheen
Bases	F-2, F-11, F-21
Vehicle Type	Acrylic
Specific Gravity	1.26 ± 0.02
Viscosity @ 27 °C	100 KU ± 2
VOC Level	<20 g/L
Drying Time ¹	Surface Dry : 30 to 40 mins. Recoat : 4 to 6 hours
Coverage ¹	130 sq.ft./L/coat
Dilution	Up to 40% with clean water

¹Drying time and coverage will vary depending upon the surface condition, degree of dilution and method of application.

Precautions

- Diluted paint must be used within 24 hours of dilution.
- Do not over-thin or over-extend the brush.
- In coastal areas, it is recommended to apply the topcoat immediately after the undercoat is dry.
- Close container after each use and store in a cool and dry place.

Application Procedure

Surface Preparation

1. New cementitious surfaces must be properly cured and sound in condition.
2. Ensure the surface is clean, dry and free from seepage, leakage, old paint, dirt, dust and any loose particles.
3. Any growth of fungus, algae or moss needs to be removed thoroughly with wire brush and water.
4. In case of dampness/waterproofing issues, repair the surface using GODRY Waterproofing Solutions.
5. Open non-structural cracks in V-groove and fill with INDICUS EASYSEAL.



Application

1. Prime the surface using INDICUS ULTRAPRIME as per the recommended application procedure.
2. Apply INDICUS ULTRACOAT Wall Putty as per the recommended method to smoothen and level the surface.
3. Apply another coat of INDICUS ULTRAPRIME and allow it to dry.
4. Apply 2-3 coats of FORTO after diluting it with clean water by up to 50%. A gap of 4 to 6 hours should be given between the coats.

Post Painting Care

- Prevent any damage to the paint film by sharp objects, overgrowth of plant or trees, etc.
- For best performance of the paint, clean the surface of all algal and fungal growth, if any, at regular intervals of six months.

* Conditions apply. Please refer INDICUS FORTO Warranty Guide for conditions and information on the warranty available at www.indicus.in/warranty.

Disclaimer: The product information and applications details given in this data sheet is meant to serve as a general guideline only. Users are advised to undertake a trial for product suitability prior to full-scale usage. There is no express or implied warranty/warranty for the results. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.